

Product Texts

Injection Molding, 50% Glass Reinforced, Heat Stabilized, Hydrolysis resistant

ISO 1043 PA66-GF50

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	15800 / 10500	MPa	ISO 527
^[C] Stress at break	225 / 160	MPa	ISO 527
^[C] Strain at break	2.7 / 4.5	%	ISO 527
^[C] Charpy impact strength, +23°C	100 / 95	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	100 / 100	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15 / 20	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12 / 13	kJ/m ²	ISO 179/1eA
^[C] Puncture - maximum force, +23°C	1100 / -	N	ISO 6603-2
^[C] Puncture - maximum force, -30°C	1000 / -	N	ISO 6603-2
^[C] Puncture energy, +23°C	4 / -	J	ISO 6603-2
^[C] Puncture energy, -30°C	3 / -	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	261 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	245 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	70 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	4.6 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.5 / *	%	Sim. to ISO 62
^[C] Density	1570 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	300	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 120	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Chemical Resistance

Hydrolytically Stable

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 280 - 300 °C

Mold temperature: 80 - 120 °C