

**KITAN A FV50H FG**

PA66-GF50

MAIP SRL

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	14800	MPa	ISO 527
Stress at break	205	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	13600	MPa	ISO 178
Flexural strength	330	MPa	ISO 178
Charpy notched impact strength, +23°C	16	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	80	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	13	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	65	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Burning rate, FMVSS, Thickness 1 mm	100	mm/min	ISO 3795 (FMVSS 302)
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Gloss, 60°	85	-	ISO 2813

Other properties	Value	Unit	Test Standard
Density	1570	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 12	h	-
Processing humidity	≤0.05	%	-
Melt temperature	280 - 310	°C	-
Mold temperature	80 - 120	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

High Gloss

**KITAN A FV50H FG**

PA66-GF50

MAIP SRL

**Delivery form**

Black

**Regional Availability**

Europe

**Special Characteristics**

Heat stabilized or stable to heat