

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	205	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	16000	MPa	ISO 178
Flexural strength	340	MPa	ISO 178
Izod notched impact strength, +23°C	16	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1580	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Mold temperature	80 - 90	°C	-

Characteristics

Processing

Injection Molding, Profile Extrusion

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Building Construction

Regional Availability

North America, Europe, Asia Pacific