

**LUMID GP2500B(W)**

PA66-GF50

LG Chem

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0035</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Break	<b>231</b>	MPa	ASTM D 638
Elongation at Break	<b>2</b>	%	ASTM D 638
Flexural Modulus	<b>14200</b>	MPa	ASTM D 790
Flexural Strength	<b>329</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 122</b>	-	ASTM D 785
Izod Impact notched, 1/4 in	<b>141</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>20</b>	E-6/K	ASTM D 696
DTUL @ 66 psi	<b>260</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>255</b>	°C	ASTM D 648
Melting Temperature	<b>260</b>	°C	ASTM D 3418
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>25</b>	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	<b>4</b>	-	ASTM D 150
Volume Resistivity	<b>1E16</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Water Absorption, 24hr	<b>0.5</b>	%	ASTM D 570
Density	<b>1570</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>80 - 100</b>	°C	-
Pre-drying - Time	<b>4 - 5</b>	h	-
Processing humidity	<b>≤0.09</b>	%	-
Melt temperature	<b>270 - 295</b>	°C	-
Mold temperature	<b>80 - 110</b>	°C	-
Zone 1	<b>260 - 270</b>	°C	-
Zone 2	<b>270 - 285</b>	°C	-
Zone 3	<b>270 - 290</b>	°C	-
Nozzle temperature	<b>270 - 295</b>	°C	-
Screw speed	<b>30 - 60</b>	rpm	-
Back pressure	<b>30 - 60</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America

**Applications**

Automotive, General Purpose