

Nylaforce® dyn B 50

PA66-GF50

Brenntag AG

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	18000 / 12500	MPa	ISO 527
Tensile Strength	270 / 175	MPa	ISO 527
Strain at break	3.3 / 5.5	%	ISO 527
Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	18 / 26	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2

Other properties	dry / cond	Unit	Test Standard
Density	1570 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Processing humidity	≤0.1	%	-
Melt temperature	250 - 320	°C	-
Mold temperature	80 - 140	°C	-
Back pressure	2 - 8	MPa	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Features

Low Odor

Regional Availability

Europe