

PA66-G50

PA66-GF50

Kingfa Sci. & Tech.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	210	MPa	ASTM D 638
Flexural Modulus	13030	MPa	ASTM D 790
Flexural Strength	300	MPa	ASTM D 790
Rockwell Hardness	R 122	-	ASTM D 785
Izod Impact notched, 1/8 in	149	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	258	°C	ASTM D 648
DTUL @ 264 psi	253	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.6	%	ASTM D 570
Density	1560	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Low Warpage

Applications

Automotive, Sports Equipment

Regional Availability

Asia Pacific