

**Product Texts**

Recycled PA66 50% glass-fibre injection moulding grade. Heat stabilized. Black colour.

The recycled material has been developed to reduce its environmental impact in comparison to traditional virgin options. Suitable for parts requiring high stiffness and good mechanical resistance.

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>16300 / 14500</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>180 / 150</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2 / 2.5</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>65 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>10 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>1E13 / -</b>	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1580 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Heat stabilized or stable to heat

**Delivery form**

Granules, Black

**Certifications**

Recycled Resin Content

**Additives**

Release agent

**Regional Availability**

Europe

**Other text information**

**Injection molding**

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

**Injection Molding Processing Parameters**

Melt Temperature  
280 - 300°C

Mold Temperature  
80 - 100°C

Injection Speed  
medium-high