

RESTRAMID A27 GF50 BK 1A0000

PA66-GF50

Polimarky Spółka Jawna

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	- / 12000	MPa	ISO 527
Strain at break	- / 3	%	ISO 527
Other properties			
Density	- / 1560	kg/m ³	ISO 1183

Characteristics**Delivery form**

Black

Regional Availability

Europe