

4MID 9A10000

PA66

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3200	MPa	ISO 527
Stress at break	80	MPa	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	5 -30	kJ/m ² °C	ISO 180/1A -
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-2 1.6	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	V-2 3.2	class mm	IEC 60695-11-10 -
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	600	-	IEC 60112
Other properties			
Density	1140	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe