

**AKROMID® A3 1 S3 grey (2955)**

PA66

Akro-Plastic GmbH

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6 / *	%	ISO 294-4, 2577
<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	2500 / -	MPa	ISO 527
Yield stress	68 / -	MPa	ISO 527
Charpy impact strength, +23°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	11 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	8 / -	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	60 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1110 / -	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Applications**

Automotive, Electrical and Electronical

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

**Regional Availability**

Europe, Asia Pacific