

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Strength	85 / 65	MPa	ISO 527
Strain at break	7.5 / 7.5	%	ISO 527
Flexural modulus, 23°C	3500 / 1500	MPa	ISO 178
Flexural modulus	1200 / -	MPa	ISO 178
Flexural modulus temperature	80	°C	-
Charpy impact strength, +23°C	135 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4.5 / 13	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 120	-	ISO 2039-2

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	265 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	244 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
Electric strength	28 / -	kV/mm	IEC 60243-1

Other properties	dry / cond	Unit	Test Standard
Water absorption	7.5 / *	%	Sim. to ISO 62
Density	1190 / -	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Flame retardant, Halogen-free

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa