

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Thermal conductivity of melt	0.32	W/(m K)	-
Spec. heat capacity of melt	2100	J/(kg K)	-
<b>Mechanical properties</b>			
	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	80 / 50	MPa	ISO 527
Yield strain	1.5 / -	%	ISO 527
Strain at break	25 / 50	%	ISO 527
Flexural modulus, 23°C	2900 / 1400	MPa	ISO 178
Flexural modulus	900 / 500	MPa	ISO 178
Flexural modulus temperature	80	°C	-
Charpy notched impact strength, +23°C	4 / 23.5	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	R 119	-	ISO 2039-2
<b>Thermal properties</b>			
	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	265 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	95 / *	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
<b>Electrical properties</b>			
	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E12 / 1E11	Ohm*m	IEC 62631-3-1
<b>Other properties</b>			
	dry / cond	Unit	Test Standard
Water absorption	8 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Special Characteristics

Heat stabilized or stable to heat

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa