

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	70	MPa	ISO 527
Yield strain	6.5	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	255	°C	ISO 11357-1/-3
Vicat softening temperature, B	230	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Water absorption	8.5	%	Sim. to ISO 62
Humidity absorption	2.5	%	Sim. to ISO 62
Density	1110	kg/m ³	ISO 1183

Characteristics

Delivery form

Natural Color

Regional Availability

Europe

Special Characteristics

High impact or impact modified