

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	2100 / 1200	MPa	ISO 527
Tensile Strength	50 / 45	MPa	ISO 527
Strain at break	>50 / -	%	ISO 527
Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	62 / 69	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	16 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	80 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Surface resistivity	* / 1E11	Ohm	IEC 62631-3-2
Electric strength	31 / -	kV/mm	IEC 60243-1
Other properties	dry / cond	Unit	Test Standard
Water absorption	1.2 / *	%	Sim. to ISO 62
Density	1080 / -	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

High impact or impact modified

Applications

Refrigeration, Sports Equipment

Regional Availability

Europe