

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8500	MPa	ISO 527
^[C] Stress at break	80	MPa	ISO 527
^[C] Strain at break	2	%	ISO 527
^[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1480	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Natural Color