

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	79	MPa	ASTM D 638
Elongation at Break	30	%	ASTM D 638
Flexural Modulus	2790	MPa	ASTM D 790
Rockwell Hardness	R119	-	ASTM D 785
Izod Impact notched, 1/8 in	48	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	221	°C	ASTM D 648
DTUL @ 264 psi	65	°C	ASTM D 648
Melting Temperature	257	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Certifications

Recycled Resin Content

Additives

Lubricants

Regional Availability

North America

Special Characteristics

Heat stabilized or stable to heat