

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>41.4</b>	MPa	ASTM D 638
Elongation at Break	<b>45</b>	%	ASTM D 638
Flexural Modulus	<b>1720</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>640</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>188</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>57</b>	°C	ASTM D 648
Melting Temperature	<b>254</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1080</b>	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	<b>0.25</b>	%	-

**Characteristics**

**Delivery form**

Pellets, Black

**Additives**

Lubricants

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

**Certifications**

Recycled Resin Content

**Regional Availability**

North America