

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>0.5</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>0.9</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>10000</b>	MPa	ISO 527
Stress at break	<b>180</b>	MPa	ISO 527
Strain at break	<b>2.5</b>	%	ISO 527
Charpy impact strength, +23°C	<b>50</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>8</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>250</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>260</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>255</b>	°C	ISO 306
Coeff. of linear therm. expansion, parallel	<b>40</b>	E-6/K	ISO 11359-1/-2

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Surface Resistivity	<b>1E12</b>	Ohm	ASTM D 257

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1410</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>90 - 100</b>	°C	-
Pre-drying - Time	<b>3</b>	h	-
Melt temperature	<b>270 - 290</b>	°C	-
Mold temperature	<b>70 - 90</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Chemical Resistance**

Oil Resistance

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe