

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	15500	MPa	ISO 527
Stress at break	215	MPa	ISO 527
Strain at break	2.2	%	ISO 527
Charpy impact strength, +23°C	65	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	241	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	259	°C	ISO 75-1/-2
Vicat softening temperature, B	250	°C	ISO 306
Other properties			
Density	1580	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	280 - 320	°C	-
Mold temperature	90 - 120	°C	-

Characteristics

Processing

Injection Molding

Features

High Gloss

Delivery form

Black

Regional Availability

Europe

Special Characteristics

Heat stabilized or stable to heat