

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8500	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Charpy impact strength, +23°C	55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	230	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2
Vicat softening temperature, B	235	°C	ISO 306

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E8	Ohm	ASTM D 257
Volume Resistivity	1E9	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1440	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	275 - 300	°C	-
Mold temperature	80 - 100	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Increased electrical conductivity