

| Mechanical properties | dry / cond | Unit | Test Standard |
|--|----------------------|-------------------|---------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 22600 / 22600 | MPa | ISO 527 |
| ^[C] Stress at break | 238 / 209 | MPa | ISO 527 |
| ^[C] Strain at break | 1.4 / 1.4 | % | ISO 527 |
| ^[C] Charpy notched impact strength, +23°C | 18 / 18 | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Thermal properties | dry / cond | Unit | Test Standard |
|---|----------------|-------|-----------------|
| ISO Data | | | |
| ^[C] Temp. of deflection under load, 1.80 MPa | 233 / * | °C | ISO 75-1/-2 |
| ^[C] Burning Behav. at 1.5 mm nom. thickn. | V-0 / * | class | IEC 60695-11-10 |
| Thickness tested | 1.5 / * | mm | - |
| Yellow Card available | yes / * | - | - |

[C]: CAMPUS

| Electrical properties | dry / cond | Unit | Test Standard |
|---|----------------|------|---------------|
| ISO Data | | | |
| ^[C] Comparative tracking index | 300 / - | - | IEC 60112 |

[C]: CAMPUS

| Other properties | dry / cond | Unit | Test Standard |
|------------------------------------|-----------------|-------------------|----------------|
| ^[C] Humidity absorption | 0.7 / * | % | Sim. to ISO 62 |
| ^[C] Density | 1860 / - | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa