

| Mechanical properties                                | dry / cond    | Unit              | Test Standard |
|--|---------------|-------------------|---------------|
| <b>ISO Data</b>                                      |               |                   |               |
| <sup>[C]</sup> Tensile Modulus                       | 11600 / 11200 | MPa               | ISO 527       |
| <sup>[C]</sup> Stress at break                       | 163 / 137     | MPa               | ISO 527       |
| <sup>[C]</sup> Strain at break                       | 2.2 / 2.2     | %                 | ISO 527       |
| <sup>[C]</sup> Charpy notched impact strength, +23°C | 10 / 10       | kJ/m <sup>2</sup> | ISO 179/1eA   |

[C]: CAMPUS

| Thermal properties                           | dry / cond | Unit  | Test Standard   |
|--|------------|-------|-----------------|
| <b>ISO Data</b>                              |            |       |                 |
| <sup>[C]</sup> Burning Behav. at thickness h | V-0 / *    | class | IEC 60695-11-10 |
| Thickness tested                             | 0.8 / *    | mm    | -               |

[C]: CAMPUS

| Electrical properties                     | dry / cond | Unit | Test Standard |
|---|------------|------|---------------|
| <b>ISO Data</b>                           |            |      |               |
| <sup>[C]</sup> Comparative tracking index | 600 / -    | -    | IEC 60112     |

[C]: CAMPUS

| Other properties                   | dry / cond | Unit              | Test Standard  |
|------------------------------------|------------|-------------------|----------------|
| <sup>[C]</sup> Humidity absorption | 1.7 / *    | %                 | Sim. to ISO 62 |
| <sup>[C]</sup> Density             | 1410 / -   | kg/m <sup>3</sup> | ISO 1183       |

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa