

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Thermal conductivity of melt	2.1	W/(m K)	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10000	MPa	ISO 527
Tensile Strength	145	MPa	ISO 527
Flexural modulus, 23°C	9000	MPa	ISO 178
Charpy impact strength, +23°C	49	kJ/m ²	ISO 179/1eU

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	1E12	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1570	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75	°C	-
Pre-drying - Time	6 - 16	h	-
Processing humidity	≤0.1	%	-
Melt temperature	290	°C	-
Mold temperature	90 - 120	°C	-
Zone 1	290 - 310	°C	-
Zone 2	290 - 310	°C	-
Zone 3	290 - 310	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Heat stabilized or stable to heat, Thermally Conductive

Applications

Automotive, IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific