

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	11000	MPa	ISO 527
Stress at break	175	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	10300	MPa	ISO 178
Charpy impact strength, +23°C	70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	8	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-40	°C	-
Rockwell hardness	L 108	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	248	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	255	°C	ISO 75-1/-2
Vicat softening temperature, B	245	°C	ISO 306
Coeff. of linear therm. expansion, parallel	21	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	15	E-6/K	ISO 11359-1/-2
Oxygen index	28	%	ISO 4589-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Dissipation factor, 1MHz	142	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	16	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	4.5	%	Sim. to ISO 62
Humidity absorption	1.1	%	Sim. to ISO 62
Density	1430	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding, Other Extrusion

### Delivery form

Pellets

### Special Characteristics

Flame retardant

### Features

Low Odor

### Regional Availability

Europe