

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11500	MPa	ISO 527
Stress at break	155	MPa	ISO 527
Strain at break	2.1	%	ISO 527
Flexural modulus, 23°C	10400	MPa	ISO 178
Izod impact strength, +23°C	55	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	245	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1470	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Flame retardant

Features

Low Odor

Regional Availability

Europe