

Product Texts

Polyamide 66, 50% glass fiber reinforced, heat-aging stabilized, for injection moulding, black

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	17500 / -	MPa	ISO 527
^[C] Stress at break	255 / -	MPa	ISO 527
^[C] Strain at break	2 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	100 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	85 / -	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E10 / -	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1570 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Black