

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	206	MPa	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638
Flexural Modulus	13730	MPa	ASTM D 790
Flexural Strength	324	MPa	ASTM D 790
Izod Impact notched, 1/8 in	137	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	250	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1560	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Chemical Resistance

General Chemical Resistance

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific