

**AKROMID® A3 GF 60 1 natural (2396)**

PA66-GF60

Akro-Plastic GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	20500 / 15800	MPa	ISO 527
Stress at break	260 / 190	MPa	ISO 527
Strain at break	2 / 2.5	%	ISO 527
Flexural modulus, 23°C	19800 / -	MPa	ISO 178
Flexural strength	400 / -	MPa	ISO 178
Charpy impact strength, +23°C	102 / 105	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	97 / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	19 / 22	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	19 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	330 / -	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	260 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	235 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.6	mm	-

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E11 / 1E8	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	600 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	3.7 / *	%	Sim. to ISO 62
Density	1710 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	320	°C	-
Mold temperature	100	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

Automotive

**Regional Availability**

Europe, Asia Pacific