

CELSTRAN®PA66-GF60-02 AD3004 Black

PA66-GF60

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	20500	MPa	ISO 527
^[C] Stress at break	266	MPa	ISO 527
^[C] Strain at break	1.5	%	ISO 527
^[C] Charpy notched impact strength, +23°C	61	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1700	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets, Black

Regional Availability

North America, Europe, Asia Pacific