

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>16400</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>260</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2</b>	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>260</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>1560</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Features**

Long fiber reinforced

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific

**Special Characteristics**

Heat stabilized or stable to heat