TECHNYL A 116ML1 WT 1133

PA66-I DOMO Engineering Plastics

Product Texts

Polyamide 66, UV-stabilized, impact modified, improved flowability, for injection moulding

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
[C] Molding shrinkage, parallel	**1.1 / ***	%	ISO 294-4, 2577
[C] Molding shrinkage, normal	**1.5 / ***	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	**2800 / -**	MPa	ISO 527
Flexural modulus, 23°C	**2700 / -**	MPa	ISO 178
Flexural strength	**95 / -**	MPa	ISO 178
[C] Charpy impact strength, +23°C	**N / -**	kJ/m²	ISO 179/1eU
[C] Charpy impact strength, -30°C	**N / -**	kJ/m²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	**10 / -**	kJ/m²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Melting temperature, 10°C/min	**262 / ***	°C	ISO 11357-1/-3
[C] Temp. of deflection under load, 1.80 MPa	**65 / ***	°C	ISO 75-1/-2
[C] Temp. of deflection under load, 0.45 MPa	**185 / ***	°C	ISO 75-1/-2
[C] Vicat softening temperature, B	**235 / ***	°C	ISO 306
[C] Burning Behav. at thickness h	**HB / ***	class	IEC 60695-11-10
Thickness tested	**0.8 / ***	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Volume resistivity	**1E13 / -**	Ohm*m	IEC 62631-3-1
[C] Surface resistivity	*** / 1E13**	Ohm	IEC 62631-3-2
[C] Comparative tracking index	**600 / -**	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Density	**1120 / -**	kg/m³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

White

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.