

Product Texts

Polyamide 66, 30% glass fiber reinforced, heat-aging stabilized, UV-stabilized, impact modified, for injection moulding

Processing/Physical Characteristics

dry / cond

Unit

Test Standard

ISO Data

Melt volume-flow rate, MVR	50 / *	cm ³ /10min	ISO 1133
Load	5 / *	kg	-
^[C] Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

dry / cond

Unit

Test Standard

ISO Data

^[C] Tensile Modulus	8400 / -	MPa	ISO 527
^[C] Stress at break	130 / -	MPa	ISO 527
^[C] Strain at break	3 / -	%	ISO 527
Flexural modulus, 23°C	8000 / -	MPa	ISO 178
Flexural strength	180 / -	MPa	ISO 178
^[C] Charpy impact strength, +23°C	65 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

dry / cond

Unit

Test Standard

ISO Data

^[C] Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties

dry / cond

Unit

Test Standard

ISO Data

^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties

dry / cond

Unit

Test Standard

^[C] Density	1340 / -	kg/m ³	ISO 1183
------------------------	----------	-------------------	----------

[C]: CAMPUS

Material specific properties

dry / cond

Unit

Test Standard

ISO Data

Viscosity number	145 / *	cm ³ /g	ISO 307, 1157, 1628
------------------	---------	--------------------	---------------------

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat