

## Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

**Zytel® 80G33HS1L NC010 is a 33% glass fiber reinforced heat stabilized polyamide 66 resin with outstanding impact resistance developed using our Super Tough technology.**

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1120	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.22	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2200	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	9E-8	m <sup>2</sup> /s	-
<sup>[C]</sup> Ejection temperature	210	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	8900 / 6200	MPa	ISO 527
<sup>[C]</sup> Stress at break	146 / 108	MPa	ISO 527
<sup>[C]</sup> Strain at break	3.7 / 7	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	* / 5300	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	* / 4300	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	97 / 98	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	106 / 100	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	20 / 28	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	18 / 17	kJ/m <sup>2</sup>	ISO 179/1eA

**ASTM Data**

Tensile Strength	145 / -	MPa	ASTM D 638
Elongation at Break	4 / -	%	ASTM D 638
Flexural Modulus	6895 / -	MPa	ASTM D 790
Flexural Strength	205 / -	MPa	ASTM D 790
Izod Impact notched, 1/8 in	219 / -	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	75 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	246 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	261 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	245 / *	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	15 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	120 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning rate, FMVSS, Thickness 1 mm	23	mm/min	ISO 3795 (FMVSS 302)
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	250	°C	ASTM D 648
Melting Temperature	263	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 1MHz	3.6 / 4.3	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	130 / 600	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13 / 1E9	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	- / 425	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	4.5 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	1.5 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1330 / -	kg/m <sup>3</sup>	ISO 1183
Density	1330	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	144 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Natural Color

### Additives

Lubricants, Release agent

### Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

### Features

Weldable

### Applications

Automotive, Sports Equipment

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa