

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3250	MPa	ISO 527
Stress at break	70	MPa	ISO 527
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	8 -30	kJ/m ² °C	ISO 180/1A -

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.6	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	HB 0.8	class mm	IEC 60695-11-10 -

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	550	-	IEC 60112

Other properties	Value	Unit	Test Standard
Humidity absorption	2	%	Sim. to ISO 62
Density	1230	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	270 - 300	°C	-
Mold temperature	70 - 110	°C	-
Feed temperature	60 - 80	°C	-
Holding pressure	50 - 100	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Special Characteristics

High impact or impact modified

Regional Availability

Europe