

Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® FR70M30V0 BK010 is a 30% mineral reinforced, flame retardant polyamide 66 resin for injection molding.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.8 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577
^[C] Ejection temperature	210	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6200 / 4000	MPa	ISO 527
^[C] Stress at break	65 / 45	MPa	ISO 527
^[C] Strain at break	2 / 3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	20 / 25	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	20 / 18	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	2.5 / 2.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	80 / *	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	145 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Burning Behav. 5V at thickness h	5VA / *	class	IEC 60695-11-20
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Oxygen index	40 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1620 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America