

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0075	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0115	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Charpy impact strength, +23°C	32	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	10.5	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	3200	MPa	ASTM D 638
Tensile Strength	65	MPa	ASTM D 638
Flexural Modulus	3000	MPa	ASTM D 790
Flexural Strength	110	MPa	ASTM D 790
Rockwell Hardness	R 115	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	245	°C	ASTM D 648
DTUL @ 264 psi	225	°C	ASTM D 648
Melting Temperature	260	°C	ASTM D 3418

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	32	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Dielectric Constant, 1 MHz	3.7	-	ASTM D 150
Volume Resistivity	1E14	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.5	%	ASTM D 570
Density	1250	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

High impact or impact modified

Regional Availability

North America, Asia Pacific

Applications

Automotive, Electrical and Electronical