

**FRCV200**

PA66-MX30

Cheng Yu Plastic Company Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.011	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	90	MPa	ASTM D 638
Flexural Strength	140	MPa	ASTM D 790
Rockwell Hardness	M 90	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-1	-	UL 94
Thickness tested	1.5	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Constant, 60 Hz	3.5	-	ASTM D 150
Surface Resistivity	>1E15	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1450	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Flame retardant

**Regional Availability**

Asia Pacific