

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Strength	80 / -	MPa	ISO 527
Strain at break	4 / -	%	ISO 527
Charpy impact strength, +23°C	38 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Other properties			
Density	1160 / -	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe