

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3	g/10min	ISO 1133
Temperature	275	°C	-
Load	0.325	kg	-
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	5800	MPa	ISO 527
Tensile Strength	115	MPa	ISO 527
Flexural modulus, 23°C	4750	MPa	ISO 178
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	245	°C	ISO 75-1/-2
Vicat softening temperature, B	240	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Other properties			
Density	1360	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Applications

Automotive, Building Construction, Electrical and Electronical

Regional Availability

Europe