

Product Texts

Extrusion, Medium/High Viscosity, Neat resin, Food Contact Quality

ISO 1043 PA6/66

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	10 / *	cm ³ /10min	ISO 1133
Temperature	230 / *	°C	-
Load	2.16 / *	kg	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	200 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	13 / *	%	Sim. to ISO 62
^[C] Humidity absorption	3.5 / *	%	Sim. to ISO 62
^[C] Density	1130 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	183 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Film Extrusion, Other Extrusion

Certifications

Food contact

Delivery form

Pellets

Regional Availability

Asia Pacific