

Product Texts

High Viscosity, Film Extrusion, Lubricated, Nucleated, Food Contact Quality

ISO 1043 PA6/66

Ideal for film extrusion processing. Food Contact quality. Enhance flexibility, transparency and stretch-ability of the film.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	2.3 / *	cm ³ /10min	ISO 1133
Temperature	230 / *	°C	-
Load	2.16 / *	kg	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	200 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	2.8 / *	%	Sim. to ISO 62
^[C] Density	1130 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	246 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Characteristics**Processing**

Film Extrusion, Other Extrusion

Features

Nucleated

Delivery form

Pellets

Certifications

Food contact

Additives

Lubricants

Regional Availability

Asia Pacific