

**SCANAMID 66.6 C22^E F**

PA666

Polykemi AB

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>75 / 55</b>	MPa	ISO 527
Yield strain	<b>5 / 25</b>	%	ISO 527
Flexural modulus, 23°C	<b>2800 / 1500</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>12 / 20</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>67 / *</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>195 / *</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>195 / *</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>1120 / -</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe, Asia Pacific

**Delivery form**

Granules