

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>3000 / 1100</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 50% strain	<b>* / 50</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>50 / *</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>50 / &gt;50</b>	%	ISO 527
Flexural modulus, 23°C	<b>2600 / 800</b>	MPa	ISO 178
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>5.5 / 40</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>242 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>67 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB / *</b>	class	IEC 60695-11-10

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>1E13 / -</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 1E12</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>26 / -</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>575 / -</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1140 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Natural Color

**Applications**

Automotive

**Special Characteristics**

High impact or impact modified