

Product Texts

Polyamide 66/6, heat-aging stabilized, halogen and red phosphorus free flame retardant, for injection moulding

| Processing/Physical Characteristics | dry / cond | Unit | Test Standard |
|--|-------------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Molding shrinkage, parallel | 1.1 / * | % | ISO 294-4, 2577 |
| ^[C] Molding shrinkage, normal | 1.1 / * | % | ISO 294-4, 2577 |

[C]: CAMPUS

| Mechanical properties | dry / cond | Unit | Test Standard |
|--|-------------------|-------------------|----------------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 3600 / 1600 | MPa | ISO 527 |
| Flexural modulus, 23°C | 3300 / 1450 | MPa | ISO 178 |
| Flexural strength | 120 / 55 | MPa | ISO 178 |
| ^[C] Charpy impact strength, +23°C | 80 / N | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy notched impact strength, +23°C | 4 / 9 | kJ/m ² | ISO 179/1eA |
| ^[C] Charpy notched impact strength, -30°C | 3.5 / - | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Thermal properties | dry / cond | Unit | Test Standard |
|---|-------------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Melting temperature, 10°C/min | 262 / * | °C | ISO 11357-1/-3 |
| ^[C] Temp. of deflection under load, 1.80 MPa | 75 / * | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 200 / * | °C | ISO 75-1/-2 |
| ^[C] Vicat softening temperature, B | 215 / * | °C | ISO 306 |
| ^[C] Burning Behav. at 1.5 mm nom. thickn. | V-0 / * | class | IEC 60695-11-10 |
| Yellow Card available | yes / * | - | - |
| ^[C] Burning Behav. at thickness h | V-0 / * | class | IEC 60695-11-10 |
| Thickness tested | 0.8 / * | mm | - |

[C]: CAMPUS

| Electrical properties | dry / cond | Unit | Test Standard |
|---|-------------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Volume resistivity | >1E13 / - | Ohm*m | IEC 62631-3-1 |
| ^[C] Surface resistivity | * / 1E14 | Ohm | IEC 62631-3-2 |
| ^[C] Comparative tracking index | 600 / - | - | IEC 60112 |

[C]: CAMPUS

| Other properties | dry / cond | Unit | Test Standard |
|-------------------------|-------------------|-------------------|----------------------|
| ^[C] Density | 1160 / - | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Special Characteristics

Flame retardant, Halogen-free, Phosphorus-free, Heat stabilized or stable to heat

Features

Copolymer