

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	18	cm <sup>3</sup> /10min	ISO 1133
Temperature	265	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	7800	MPa	ISO 527
Stress at break	135	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	6200	MPa	ISO 178
Flexural strength	195	MPa	ISO 178
Charpy impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	200	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
Temp. of deflection under load, 8.00 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, B	210	°C	ISO 306
Coeff. of linear therm. expansion, parallel	40	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Glow Wire Flammability Index (GWFI)	750	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 100Hz	3.8	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.6	-	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	26	kV/mm	IEC 60243-1
Comparative tracking index	250	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	0.4	%	Sim. to ISO 62
Density	1470	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Delivery form

Natural Color

### Regional Availability

North America, Europe