

Product Texts

Product-nomenclature: ISO 16396-PA6T/66,GF15,M1H,C12-060

Co Polyamide

Partially aromatic Polyamide

Product Attributes

Improved alcohol resistance, Improved impact resistance, Improved heat resistance

Markets**Automotive**

Air intake systems, Compressed air systems, Hydraulic systems, Automotive electr. and electronics, lighting, Fuel systems, Powertrain and Chassis, Interior

Electricals & Electronics

Electrical appliances, Electrical equipment, Connectors, Energy distribution, Mobile phones and other portable devices

Industry & Consumer goods

Hydraulics & Pneumatics, Mechanical Engineering, Power transmission, Tools & Accessories

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6000 / 5800	MPa	ISO 527
^[C] Stress at break	125 / 100	MPa	ISO 527
^[C] Strain at break	3 / 3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	65 / 55	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	45 / 40	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10 / 10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	5 / 5	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	82 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	310 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	265 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	100 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	30 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	75 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E10 / 1E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E12	Ohm	IEC 62631-3-2
^[C] Electric strength	33 / 32	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 575	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	5.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1240 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Granules, Black

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Copolymer

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa