

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955
Mechanical properties			
	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	120 / 110	MPa	ASTM D 638
Flexural Modulus	6000 / 5500	MPa	ASTM D 790
Flexural Strength	190 / 170	MPa	ASTM D 790
Rockwell Hardness	M 105 /	-	ASTM D 785
Izod Impact notched, 1/8 in	50 / 70	J/m	ASTM D 256
Thermal properties			
	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-
Coefficient of Thermal Expansion, MD	34	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	55	E-6/K	ASTM D 696
DTUL @ 264 psi	290	°C	ASTM D 648
Melting Temperature	320	°C	ASTM D 3418
Glass Transition Temperature	125	°C	ASTM E 1356
Electrical properties			
	dry / cond	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	25 / -	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.02 / -	-	ASTM D 150
Dielectric Constant, 1 MHz	4.2 / -	-	ASTM D 150
Volume Resistivity	>1E15 / -	Ohm*cm	ASTM D 257
Other properties			
	Value	Unit	Test Standard
Water Absorption, 24hr	0.4	%	ASTM D 570
Density	1300	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
	Value	Unit	Test Standard
Pre-drying - Temperature	110	°C	-
Pre-drying - Time	2 - 6	h	-
Mold temperature	90 - 140	°C	-
Feed temperature	50 - 90	°C	-
Zone 1	315 - 330	°C	-
Zone 2	320 - 335	°C	-
Zone 3	325 - 340	°C	-
Nozzle temperature	325 - 340	°C	-
Screw speed	150	rpm	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific