

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4 / *	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	2900 / 1400	MPa	ISO 527
Yield stress	75 / 55	MPa	ISO 527
Strain at break	>50 / >50	%	ISO 527
Flexural modulus, 23°C	2600 / -	MPa	ISO 178
Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	11 / 23	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	10 / 21	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	R 118	-	ISO 2039-2
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190 / *	°C	ISO 75-1/-2
Vicat softening temperature, B	240 / *	°C	ISO 306
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
Comparative tracking index	600 / -	-	IEC 60112
<b>Other properties</b>			
Density	1120 / -	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	40 - 80	°C	-

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe, Asia Pacific

### Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather