

ECOMID® A HH J8 BK 9005/1

PA66

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2940	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	74	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	216	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1110	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Black

Certifications

Recycled Resin Content

Special Characteristics

Heat stabilized or stable to heat