

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.9 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2800 / 1450	MPa	ISO 527

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	71 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	227 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	7.6 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.2 / *	%	Sim. to ISO 62
^[C] Density	- / 1090	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form
Black

Regional Availability
North America

Certifications
Recycled Resin Content